FIBERTEC Reinforcing the plastics industry

35 Scotland Boulevard ● Bridgewater, MA 02324 ● 508-697-5100 ● Fax 508-697-7140 ● www.fibertecinc.com

TYPICAL PRODUCT SPECIFICATION WOLLASTONITE 905S (CALCIUM METASILICATE)

CHEMICAL COMPOSITION		MINERAL DE	MINERAL DESCRIPTION		
COMPONENT CaO SiO ₂ Fe_2O_3 Al_2O_3 MgO	WEIGHT % 46.50 52.20 0.20 0.25 0.20	occuring, non	Wollastonite is a naturally occuring, non-metallic, acicular (needle-shape) mineral.		
L.O.I. (inorganic)	< 1.00	TYPICAL PR	TYPICAL PROPERTIES		
L.O.I. (organic) Moisture	< 0.05 < 0.10	Appearance Morphology	Appearance		
MORPHOLOGY		•	pH Specific Gravity		
Length (µ) ¹	50.0	•	Refractive Index		
Diameter (μ) ¹	9.0	Moh's Hardness		4 – 5	
Aspect Ratio ²	5.0	Coef. of Expansion		6.5 x 10 ⁻⁴ 1,540 °C	
D50 (µ) ³	18.0	Melting Point	•		
Surface Area (m ² /g) BET	1.1	G.E. Brightne	G.E. Brightness		
WET SCREEN ANALYSIS DENSI		DENSITY & OIL ABSO	TY & OIL ABSORPTION		
% -100	100	Loose Bulk Density	(g/cc)	0.74 +/- 0.11	
% -200	99.9		(lbs/ft ³)	46.2 +/- 6.9	
% -325	99.4				
% -400	96.1	Tapped Bulk Density	(g/cc)	1.11 +/- 0.17	
% -500	88.5		(lbs/ft ³)	69.3 +/- 10.4	
		Oil Absorption		35	

Final determination of the suitability of the material for the use contemplated is the sole responsibility of the user. No warranty is expressed or implied, and the manufacturer's only obligation shall be to replace such quantity of the product proven to be defective.

¹ Microscopic measurement average of 100 counts ² Average of 100 individual aspect ratios ³ Malvern Mastersizer